

Products description

Metallic polyurethane material for heat transfer applications.

Thickness : 60 microns (USA : 2,4 mil).

Carrier : self-adhesive and transparent polyester.

Suitable for

HOTMARK Metallic : Cotton, polyester, acrylic and similar fibres.

Application advises

- 1) Cut the material in reverse with a flex blade.
- 2) Weed the excess material.
- 3) Heat press the image on the garment with its polyester carrier protected by a silicone paper at 140°C (USA : 280°F) – 15-20 seconds – medium pressure.
- 4) Peel the carrier off when cold.

Maintenance

Always respect the instructions mentioned on garments.

After heat pressing, wait 24 hours before the first wash.

Washing : hand and cold washing - without bleach or any aggressive washing products.

Dried cleaning : no

Ironing : backside

Storage of the roll : vertically, one year in a dry room, 15-30°C (USA : 60-85°F), protected from sunlight.

Caution

Be careful with the metallic quality : Never heat press twice this product.

Those recommendations are based on our own experiences.

We always recommend making trials before starting standard production.

July 2009

To Order HotMark Metallic visit
www.Specialty-Graphics.com
or call 1-888-330-6172