



Produced with: TECHNI-PRINT® EZP



Produced with: TECHNI-PRINT® EZP

### TECHNI-PRINT® EZP Brand

For transfer to all white and light colored fabrics, mousepads, coasters, puzzles, and leather goods.

**TECHNI-PRINT® EZP** Heat Transfer Paper is for transferring photos and graphics to white and light colored fabrics, is easy to use yet gives crisp vibrant images regardless of the model of the laser printer or copier. Also Indigo® certified for the 7000 – 1000 series of printers.



- Heat Press required
- Image should be printed in **REVERSE**

**TAEH**

REVERSE/MIRRORED

NEENAH COLDENHOVE Brands for Laser Printers	Product ID	Natural & 50/50 Fabric	Poly Fabric	Hard Surface	Mesh Screen 85-230	Works well with Photos	Certified for HP Indigo Presses	Prepress*	Peel Temperature				Cover with Parchment	Repress and Stretch	Weedable
									Hot	Warm	Cold	Hand Iron			
TECHNI-PRINT® EZP	9868P0	✓	★	★		✓	✓	✓	✓	✓	✗	✓	✗	✗	★
PHOTO-TRANS SC®	0908P0	✓	★	★		✓	✓	✓	✓						
IMAGE CLIP® Laser Light	9770P0	✓	★	★			✓	✓	✓ 1st		✓ 2nd				✓ Self
TECHNI-PRINT® HS	9842P0			✓		✓	✓				✓				★

✓ Yes [✗ If, • Then] ★ With special settings, dictated by the design

\*Prepress to remove wrinkles and moisture.

**OKI**  
SUPPORTED



**PRINTING INSTRUCTIONS:**

1. Print the image in reverse/mirrored format using a Heavy paper mode.
2. Trim away the unprinted areas of the transfer if desired.



Press Settings should be  
375°F/190°C with medium to  
heavy pressure for 30 seconds

**PRE-TRANSFERRING INSTRUCTIONS:**

1. Prepare the garment/fabric by ensuring the surface is clean, dry, and wrinkle free by using a lint brush and your heat press.

**TRANSFERRING INSTRUCTIONS:**

1. Place the transfer on top of the garment with the print image against the fabric.
2. Press 30 seconds at 375°F/190°C using medium to heavy pressure (40 to 70 psi/3 to 5 bar).
3. For best results leave on the heat press, wait 10 to 15 seconds depending upon the fabric and then peel the paper in a smooth even motion (hot peel).
4. To improve the feel or "hand" and get even better wash durability, stretch the garment in all directions while still hot.
5. If desired, wait and peel the paper after cooling completely (cold peel). This method gives a stiffer "hand" but it is quicker and works well for hard surfaces.
6. You can then improve the softness and get even better wash durability by covering the image with parchment paper, repressing for 10 seconds and immediately stretching in all directions while still hot.

**Xtra SOFT FABRIC METHOD:**

1. Alter pressing step to 10 to 15 seconds at 375°F/190°C using medium to heavy pressure (40 to 70 psi/3 to 5 bar).
2. Remove from press and peel the paper after cooling (Do not stretch).
3. Place the garment back on the heat press and cover the image with parchment paper.
4. Press using medium to heavy (40 to 70 psi/3 to 5 bar) pressure for 25 seconds to fully bond the image to the garment.
5. Remove the parchment paper and immediately stretch the garment in all directions to soften, improving the "hand", and also improving the wash durability.

**WASHING INSTRUCTIONS:**

Turn garment inside out and wash in cold water using a mild detergent. Do not use bleach. Dry on low-heat setting. If you intend to iron the transferred area, ensure that the image is covered with parchment paper before ironing.

**IMPORTANT:** Printers and heat presses vary in accuracy. We have tested our products with numerous printers and presses with excellent results. Nonetheless, we recommend that you test the paper in your equipment to ensure the best results. Neenah's maximum obligation shall be to replace any paper that has proven to be defective.



For more information about Neenah Paper Heat Transfer Papers:  
North America: 800.344.5287 | Outside North America: 906.387.2700  
neenahheat.com | neenah.heat@neenah.com | @neenahheat

