



# DIGITAL MEDIA APPLICATION INSTRUCTIONS

## ColorPrint Easy

For Use On: 100% cotton | Poly/cotton blends | 100% polyester | Leather



### Print and Cut Instructions:

- Print, cut, and weed material
- No dry time required!
- Mask with TTD Easy mask or TTD High Tack Mask

### Application Instructions:

- Preheat garment for 2-3 seconds
- Apply design at 300°F / 149°C
- Use medium pressure for 15 seconds
- Peel carrier warm

### Laundering:

- Wait 24 hours before first wash
- Machine wash warm or cold with mild detergent
- Do not bleach or dry clean
- Dry on normal dryer setting

**Compatible with Eco-Solvent and Solvent Inks - Not for use with Inkjet or Laser printers**

## ColorPrint Extra PU

For Use On: 100% Nylon | 100% cotton | Poly/cotton blends | 100% polyester | Leather

### Print and Cut Instructions:

- Print, cut, and weed your design
- No dry time required!
- Mask with TTD Easy mask or TTD High Tack Mask

### Application Instructions:

- Preheat garment for 2-3 seconds
- Apply design at 305°F / 150°C
- Use medium pressure for 15 seconds
- Peel carrier hot or warm

### Laundering:

- Wait 24 hours before first wash
- Machine wash cold with mild detergent
- Do not bleach or dry clean
- Wash inside-out for best results

**Compatible with Eco-Solvent, Solvent, and Latex Inks - Not compatible with Inkjet or Laser printers**

## ColorPrint PU (Matte/Gloss)

For Use On: 100% cotton | Poly/cotton blends | 100% polyester | Leather | Lycra®/Spandex



### Print and Cut Instructions:

- Set heater/dryer to 113°F/45°C
- If heavy saturation ink, dry 1 hour before cutting
- Print, cut, and weed material
- Mask with TTD Easy mask or TTD High Tack Mask

### Application Instructions:

- Preheat garment for 2-3 seconds
- Apply design at 295°F / 146°C
- Use medium pressure for 15-20 seconds
- Peel carrier hot

### Laundering:

- Wait 24 hours before first wash
- Machine wash warm or cold with mild detergent
- Do not bleach or dry clean
- Dry on normal dryer setting

**Compatible with Eco-Solvent, Solvent, and Latex Inks - Not compatible with Inkjet or Laser printers**

## DigiBrick™

For Use On: 100% cotton | 100% polyester | Poly/cotton blends



### Print and Cut Instructions:

- Print, cut and weed your design
- Mask with TTD High Tack Mask

### Application Instructions:

- Preheat garment for 2-3 seconds
- Apply design at 311°F / 155°C
- Use medium/firm pressure for 25 seconds
- Peel carrier hot

### Laundering:

- Wait 24 hours before first wash
- Machine wash cold with mild detergent
- Do not bleach or dry clean
- Dry on low dryer setting

**Compatible with Eco-Solvent and Solvent Inks - Not compatible with Inkjet or Laser printers**

## EasyPSV™ Printable

For Use On: Glass | Wood | Plastic | Metal | Ceramic



### Print and Cut Instructions:

- Print and cut your design (do not reverse/mirror)
- Weed excess vinyl
- Remove application tape's paper liner and place on top of EasyPSV
- Burnish with a Squeegee
- Place on desired object and burnish with a squeegee
- peel away the application tape

### Application Instructions:

- Preheat garment for 2-3 seconds
- Apply design at 311°F / 155°C
- Use medium/firm pressure for 5 seconds
- Peel carrier Hot
- Re-cover design and press for 20 seconds

### Laundering:

- Wait 24 hours before first wash
- Machine wash cold with mild detergent
- Do not bleach or dry clean
- Dry on low dryer setting

**Compatible with Eco-Solvent, Solvent, Latex, and Mimaki UV Inks - Not compatible with Inkjet or Laser printers**

## Hi-5 Print Matte

For Use On: 100% cotton | Poly/cotton blends | 100% polyester



### Print and Cut Instructions:

- Print, cut, and weed your design
- Mask with TTD Easy Mask or TTD High Tack Mask

### Application Instructions:

- Preheat garment for 2-3 seconds
- Apply design at 250°F / 120°C
- Use medium pressure for 5 seconds
- Peel carrier hot

### Laundering:

- Wait 24 hours before first wash
- Machine wash cold with mild detergent
- Do not bleach or dry clean
- Dry on normal dryer setting

**Compatible with Eco-Solvent, Solvent, and Latex Inks - Not compatible with Inkjet or Laser printers**

## SparklePrint™

For Use On: 100% cotton | 100% polyester | Poly/cotton blends



### Print and Cut Instructions:

- Print, cut, and weed material
- No dry time required!
- Mask with TTD Easy mask or TTD High Tack Mask

### Application Instructions:

- Preheat garment for 2-3 seconds
- Apply design at 311°F / 155°C
- Use medium/firm pressure for 15 seconds
- Peel carrier hot

### Laundering:



- Wait 24 hours before first wash
- Machine wash cold with mild detergent
- Dry on low dryer setting
- Do not bleach or dry clean
- Wash inside-out for best results

**Compatible with Eco-Solvent, Solvent, and Latex Inks - Not compatible with Inkjet or Laser printers**





# DIGITAL MEDIA APPLICATION INSTRUCTIONS

<b>S-Print™</b> (Matte) For Use On: 100% cotton   Poly/cotton blends   100% polyester   Spandex 		
<p><b>Print and Cut Instructions:</b></p> <ul style="list-style-type: none"> <li>• Print, cut, and weed your design</li> <li>• Mask with TTD Easy Mask or TTD High Tack Mask</li> </ul>	<p><b>Application Instructions:</b></p> <ul style="list-style-type: none"> <li>• Preheat garment for 2-3 seconds</li> <li>• Cover design with Heat Transfer Cover Sheet</li> <li>• Apply design at 248°F / 120°C</li> <li>• Use medium pressure for 10-15 seconds</li> <li>• Peel carrier hot</li> </ul>	<p><b>Laundering:</b></p> <ul style="list-style-type: none"> <li>• Wait 24 hours before first wash</li> <li>• Machine wash warm or cold with mild detergent</li> <li>• Do not bleach or dry clean</li> <li>• Dry on normal dryer setting</li> </ul>
<b>Compatible with Eco-Solvent and Solvent Inks - Not compatible with Inkjet or Laser printers</b>		
<b>Sublithin® Soft</b> For Use On: Sublimated   polyester 100% cotton   Poly/cotton blends   100% polyester 		
<p><b>Print and Cut Instructions:</b></p> <ul style="list-style-type: none"> <li>• Print, cut, and weed your design</li> <li>• Mask with TTD Easy Mask</li> </ul>	<p><b>Application Instructions:</b></p> <ul style="list-style-type: none"> <li>• Preheat garment for 2-3 seconds</li> <li>• Apply design at 265°F / 130°C</li> <li>• Use medium pressure for 15 seconds</li> <li>• Peel carrier warm</li> </ul>	<p><b>Laundering:</b></p> <ul style="list-style-type: none"> <li>• Wait 24 hours before first wash</li> <li>• Machine wash cold with mild detergent</li> <li>• Do not bleach or dry clean</li> <li>• Hang item to dry</li> </ul>
<b>Compatible with Eco-Solvent, Solvent and Latex Inks - Not compatible with Inkjet or Laser printers</b>		

